

Topic:Rust Preventive

980Oils Products	Lube Kote M81
Applications	Dipping
Customer /Location	PT. SAGA HIKARI TEKNINDO, Cikarang
Previous Lube/Fluids	SK DNS-1
Material	SCM 435
Process/Machines	Forming
Customer Requirements	No rust for 3 months

Issue/Problems :

- Cost Improvement

Solutions :

- 1) Survey Process On-site.
- 2) Take existing product for lab comparison.



Summary :

- Already pass on trial process, using Salt Spray Test.
- No rust after 12 hours on SST.
- Customer arranged to mix with kerosene 1: 2 and result still good.